




Technical Specification Sheet

Antique Heart Pine - Vertical Grade

Vertical Grain Antique Heartpine Flooring consists of 100 percent heartwood milled from beams laced with very tight growth rings and has very few knot and nail hole content. Because of its rarity, uniformity and strength that rivals oak, Vertical Grain is considered the highest quality and is suitable for even the most formal setting.



Overall Specification

Species:	Antique Heart Pine Vertical Grain
Cut:	Vertical Grain
Texture:	Smooth
Janka Hardness:	1,225
Flame Spread Class Rating:	Class III (Class C)
Standard Millwork:	Tongue & Groove, End matched
Optional Mill:	Ship Lap Profile

Detailed Specification

	Solid	Engineered
Thickness:	3/4"	3/4" or 5/8"
Width:	2.5"-5" (inquire about wider)	2.5"-5" (inquire about wider)
Random Lengths:	2'-12'	2'-10'
Edges:	Square or Microbevel	Square or Microbevel

**Inherent characteristics in reclaimed wood are not considered defects

*Janka Rating: is provided from similar tested products

*Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. HPCo. Products have not been tested but are expected to be close to actual measurements on comparable wood species.

*We can Fire Tread to Class A for Interior Applications for additional upcharge, contact for details.



Technical Specification Sheet

Antique Heart Pine - Select Grade

Select Antique Heartpine Flooring is milled from beams consisting of 95 – 100 percent heartwood with tight growth ring patterns and amber-golden color variations, combined with the occasional solid knot and nail hole. Select Grade is Heartpine Company's most versatile flooring, gracing any floor with elegance and character.



Overall Specification

Species:	Antique Heart Pine Select Grade
Cut:	Select
Texture:	Smooth
Janka Hardness:	1,225
Flame Spread Class Rating:	Class III (Class C)
Standard Millwork:	Tongue & Groove, End matched
Optional Mill:	Ship Lap Profile

Detailed Specification

	Solid	Engineered
Thickness:	3/4"	3/4" or 5/8"
Width:	2.5"-12" (inquire about wider)	2.5"-12" (inquire about wider)
Random Lengths:	2'-12'	2'-10'
Edges:	Square or Microbevel	Square or Microbevel

**Inherent characteristics in reclaimed wood are not considered defects

*Janka Rating: is provided from similar tested products

*Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. HPCo. Products have not been tested but are expected to be close to actual measurements on comparable wood species.

*We can Fire Tread to Class A for Interior Applications for additional upcharge, contact for details.



Technical Specification Sheet

Antique Heart Pine - Traditional Grade

Traditional Antique Heartpine Flooring is milled from beams and decking consisting of 85 – 100 percent heartwood with predominantly red, amber and slightly golden color variations, with an occasional aberration from a paler section of sap wood. Traditional Grade also contains the more frequent appearance of larger solid knots, as well as more nail hole content to showcase the wood’s full history.



Overall Specification

Species:	Antique Heart Pine Traditional Grade
Cut:	Traditional
Texture:	Smooth
Janka Hardness:	1,225
Flame Spread Class Rating:	Class III (Class C)
Standard Millwork:	Tongue & Groove, End matched
Optional Mill:	Ship Lap Profile

Detailed Specification

	Solid	Engineered
Thickness:	3/4"	3/4" or 5/8"
Width:	2.5"-12" (inquire about wider)	2.5"-12" (inquire about wider)
Random Lengths:	2'-12'	2'-10'
Edges:	Square or Microbevel	Square or Microbevel

**Inherent characteristics in reclaimed wood are not considered defects

*Janka Rating: is provided from similar tested products

*Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. HPCo. Products have not been tested but are expected to be close to actual measurements on comparable wood species.


*We can Fire Tread to Class A for Interior Applications for additional upcharge, contact for details.



Technical Specification Sheet

Antique Heart Pine - Naily Grade

Naily Antique Heartpine Flooring is milled from outside cuts of beams and decking consisting of 70 – 100 percent heartwood. The color of this grade tends to feature red highlights, along with the expected amber and slightly golden hues. The character of this wood is varied. Not only will you find solid knots and heavy nail hole patterns but one might find saw marks, scars from abuse and even some leftover old paint. Naily Grade may be the most environmentally sound flooring we offer, because we waste essentially nothing of the raw material in creating the final product.



Overall Specification

Species:	Antique Heart Pine Naily Grade
Cut:	Naily
Texture:	Smooth
Janka Hardness:	1,225
Flame Spread Class Rating:	Class III (Class C)
Standard Millwork:	Tongue & Groove, End matched
Optional Mill:	Ship Lap Profile

Detailed Specification

	Solid	Engineered
Thickness:	3/4"	3/4" or 5/8"
Width:	2.5"-12"	2.5"-12"
Random Lengths:	2'-12'	2'-10'
Edges:	Square or Microbevel	Square or Microbevel

**Inherent characteristics in reclaimed wood are not considered defects

*Janka Rating: is provided from similar tested products

*Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. HPCo. Products have not been tested but are expected to be close to actual measurements on comparable wood species.


*We can Fire Tread to Class A for Interior Applications for additional upcharge, contact for details.



Technical Specification Sheet

Antique Heart Pine - Hit/Miss

Antique Heart Pine - Hit/Miss combines the gorgeous character of heart wood with our custom milling hit/miss process, to give a gorgeous texture to the face. Under the texture shines the beautiful depth of color in Heart Pine.



Overall Specification

Species:	Antique Heart Pine - Hit/Miss
Cut:	Textured Face
Texture:	Distressed
Janka Hardness:	1,225
Flame Spread Class Rating:	Class III (Class C)
Standard Millwork:	Tongue & Groove, End matched
Optional Mill:	Ship Lap Profile

Detailed Specification

	Solid	Engineered
Thickness:	3/4"	3/4" or 5/8"
Width:	2.5"-12"	2.5"-12"
Random Lengths:	2'-12'	2'-10'
Edges:	Square or Microbevel	Square or Microbevel

**Inherent characteristics in reclaimed wood are not considered defects

*Janka Rating: is provided from similar tested products

*Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. HPCo. Products have not been tested but are expected to be close to actual measurements on comparable wood species.

*We can Fire Tread to Class A for Interior Applications for additional upcharge, contact for details.



Technical Specification Sheet

Antique Pine - Hit/Miss, Tobacco Wood

Tobacco barns were once a common site on farms throughout Virginia and The Carolinas. Used to cure the tobacco produced on the farms, the wooden material would take on a leathered look over time from housing the curing process. In milling this floor, we have taken great care to preserve than natural patina, saw kerf marks, and the other characteristics that make this floor unique—a unique mixture of browns and reds, along with occasional nail holes and a history that becomes the centerpiece of any home.



Overall Specification

Species:	Antique Hit-Miss Tobaccowood
Cut:	Textured Face
Texture:	Distressed
Janka Hardness:	1,225
Flame Spread Class Rating:	Class III (Class C)
Standard Millwork:	Tongue & Groove, End matched
Optional Mill:	Ship Lap Profile

Detailed Specification

	Solid	Engineered
Thickness:	3/4"	3/4" or 5/8"
Width:	2.5"-12"	2.5"-12"
Random Lengths:	2'-12'	2'-10'
Edges:	Square or Microbevel	Square or Microbevel

**Inherent characteristics in reclaimed wood are not considered defects

*Janka Rating: is provided from similar tested products

*Flame Spread Class Rating, Flame Spread Index Data and Smoke Developed Index based on report from American Wood Council - 2017. HPCo. Products have not been tested but are expected to be close to actual measurements on comparable wood species.

*We can Fire Tread to Class A for Interior Applications for additional upcharge, contact for details.